

NanoScreen™ Soft Lack



Technisches Datenblatt

Intended use: Silicone lacquer for coating earmolds and ear impressions

Manufacturer: Dreve Otoplastik GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	chemical term
1	polydimethyl siloxane
2	filling materials
3	auxiliaries
4	acetoxysilane vulcanizer in heptane
5	toluene
6	nanosstructural silver particles

Characteristic: Heavy body one component silicone rubber, vulcanizes under the impact of air humidity and splitting of acetic acid to a rubber-elastic resin.

Color: clear, transparent

Properties:

Density (unvulcanized): 0.84 g/cm³ at 20 °C (DIN 53479 A)

Curing: 30 min at 23 °C, 50 - 60 % RLF

Dreve Otoplastik GmbH

Max-Planck-Str. 31

59423 Unna / Germany

Tel.: 02303 / 8807-0

Fax: 02303 / 82909

info@dreve.de

www.dreve.com